

## Technical Data Sheet

# DuCare<sup>®</sup> W 50 EM

## Polypropylene Homopolymer

### Description

DuCare W 50 EM is a polypropylene homopolymer (produced with a phthalate-free catalyst) with a narrow to medium molecular weight distribution. The product shows a very high flowability and good stiffness.

### Applications

DuCare W 50 EM is suitable for: (thin-walled) injection moulding applications, compounding, packaging applications for the life science market, like PCR tips and medical packaging etc.

### Quality, Environment and Safety Regulations

Material Safety Data Sheets and other regulatory documents are available on our web site <http://www.ducorchem.com>

Properties		Method	Typical Value*	Unit
<b>Physical</b>				
Melt Flow Rate	(230 °C / 2.16 kg)	ISO 1133	75	g/10 min
<b>Mechanical</b>				
Tensile Modulus	(1 mm/min)	ISO 527-2	1600	MPa
Tensile Stress at Yield	(50 mm/min)	ISO 527-2	35	MPa
Tensile Strain at Yield	(50 mm/min)	ISO 527-2	8	%
Tensile Strain at Break	(50 mm/min)	ISO 527-2	20	%
Charpy Impact Strength, notched	(+23 °C)	ISO 179/1eA	2.2	kJ/m <sup>2</sup>
Charpy Impact Strength, unnotched	(+23 °C)	ISO 179/1eU	80	kJ/m <sup>2</sup>
Izod impact strength, notched	(+23 °C)	ISO 180/1A	2.4	kJ/m <sup>2</sup>
<b>Thermal</b>				
Melting Point, DSC		ISO 3146	163	°C
Heat Deflection Temperature	(1.8 MPa)	ISO 75-2	55	°C
Heat Deflection Temperature	(0.45 MPa)	ISO 75-2	85	°C
Vicat Softening Temperature	(10 N)	ISO 306	154	°C
Vicat Softening Temperature	(50 N)	ISO 306	90	°C
<b>Other Properties</b>				
Density		ISO 1183	0.91	g/cm <sup>3</sup>

\* Typical values; not to be construed as specifications

Ducor Petrochemicals B.V., POB 1038, 3180AA Rozenburg ZH, the Netherlands  
 Web: <http://www.ducorchem.com/>  
 Email: [sales@ducorchem.com](mailto:sales@ducorchem.com)

Last updated: Jan 2023

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Ducor Petrochemicals extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.