

Technical Data Sheet

DuPure[®] E 50

Polypropylene Homopolymer

Description

DuPure E 50 is a polypropylene homopolymer (produced with a phthalate-free catalyst), formulated with a general purpose additivition package.

Applications

DuPure E 50 is suitable for: extrusion, general purpose injection moulding, e.g. caps & closures.

Quality, Environment and Safety Regulations

Material Safety Data Sheets and other regulatory documents are available on our web site <http://www.ducorchem.com>.

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(230 °C / 2.16 kg)	ISO 1133	2.1	g/10 min
Mechanical				
Tensile Modulus	(1 mm/min)	ISO 527-2	1450	MPa
Tensile Stress at Yield	(50 mm/min)	ISO 527-2	33	MPa
Tensile Strain at Yield	(50 mm/min)	ISO 527-2	9	%
Tensile Strain at Break	(50 mm/min)	ISO 527-2	> 50	%
Charpy Impact Strength, notched	(+23 °C)	ISO 179/1eA	5.0	kJ/m ²
	(-30 °C)	ISO 179/1eA	1.5	kJ/m ²
Charpy Impact Strength, unnotched	(+23 °C)	ISO 179/1eU	No Break	kJ/m ²
	(-30 °C)	ISO 179/1eU	17	kJ/m ²
Izod Impact Strength, notched	(+23 °C)	ISO 180/1A	4.5	kJ/m ²
	(-30 °C)	ISO 180/1A	1.4	kJ/m ²
Ball Indentation Hardness (H 358/30)		ISO 2039-1	72	MPa
Thermal				
Melting Point, DSC		ISO 3146	163	°C
Heat Deflection Temperature	(1.8 MPa)	ISO 75-2	55	°C
Heat Deflection Temperature	(0.45 MPa)	ISO 75-2	85	°C
Vicat Softening Temperature	(10 N)	ISO 306	154	°C
Vicat Softening Temperature	(50 N)	ISO 306	90	°C
Other Properties				
Haze	(1 mm plaque)	ASTM D1003	60	%
Density		ISO 1183	0.91	g/cm ³

* Typical values; not to be construed as specifications