

DuPure[®] QR 50

Polypropylene Random Copolymer

Description

DuPure QR 50 is a polypropylene random copolymer (produced with a phthalate-free catalyst) for extrusion applications (e.g. manufacturing highly transparent films with good weldability). The product does not contain any functional additives (like a slip or an anti-blocking agent).

Applications

DuPure QR 50 is suitable for: cast film with broad sealing range, lamination films, water-quenched blown films, and injection moulded products.

Quality, Environment and Safety Regulations

Material Safety Data Sheets and other regulatory documents are available on our web site <http://www.ducorchem.com>.

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(230 °C/ 2.16 kg)	ISO 1133	10	g/10 min
Mechanical				
Tensile Modulus	(1 mm/min)	ISO 527-2	1000	MPa
Tensile Stress at Yield	(50 mm/min)	ISO 527-2	27	MPa
Tensile Strain at Yield	(50 mm/min)	ISO 527-2	12	%
Tensile Strain at Break	(50 mm/min)	ISO 527-2	> 100	%
Charpy Impact Strength, notched	(+23 °C)	ISO 179/1eA	6.0	kJ/m ²
Charpy Impact Strength, unnotched	(+23 °C)	ISO 179/1eU	No Break	kJ/m ²
Izod Impact Strength, notched	(+23 °C)	ISO 180/1A	7.0	kJ/m ²
Thermal				
Melting Point, DSC		ISO 3146	145	°C
Other Properties				
Density		ISO 1183	0.91	g/cm ³

* Typical values; not to be construed as specifications

Ducor Petrochemicals B.V., POB 1038, 3180AA Rozenburg ZH, the Netherlands
 Web: <http://www.ducorchem.com/>
 Email: sales@ducorchem.com

Last updated: October 2023