

DuPure[®] T 01 NP

Polypropylene Homopolymer – Non Pelletized

Description

DuPure T 01 NP is a non-pelletized polypropylene homopolymer (produced with a phthalate-free catalyst) supplied in the form of unstabilized free flowing powder. The spherical shape and narrow particle size distribution (with low fines content) makes DuPure T 01 NP very suitable for mixing with additives, liquids, fillers and (color-)pigments, and for compounding with other polymers (e.g. S(E)BS, EPDM resins).

Applications


DuPure T 01 NP is suitable for: Compounding, Masterbatches

Quality, Environment and Safety Regulations

Material Safety Data Sheets and other regulatory documents are available on our web site <http://www.ducorchem.com>

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(230 °C/ 2.16 kg)	ISO 1133	25**	g/10 min
Mechanical				
Tensile Modulus	(1 mm/min)	ISO 527-2	1600	MPa
Thermal				
Melting Point, DSC		ISO 3146	163	°C
Other Properties				
Density		ISO 1183	0.91	g/cm ³

Particle Size Distribution



* Typical values; not to be construed as specifications

** The indicated Melt Flow Rate (MFR) is obtained by premixing the non-pelletized resin with an additive blend, consisting of: 0.25-0.5% Primary (e.g. phenolic) anti-oxidant, 0.25-0.5% Secondary (e.g. phosphite) anti-oxidant, and 0.05 - 0.1% Acid scavenger (e.g. Calcium stearate), prior to the MFR measurement

Ducor Petrochemicals B.V., POB 1038, 3180AA Rozenburg ZH, the Netherlands

Last updated: February 2025

Web: <http://www.ducorchem.com/>

Email: sales@ducorchem.com

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Ducor Petrochemicals extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.