

Technical Data Sheet

DuPure[®] T 88 E

Polypropylene Homopolymer

Description

DuPure T 88 E is a polypropylene homopolymer fibre grade (produced with a phthalate-free catalyst), characterized by high flowability, a narrow to medium molecular weight distribution, and medium crystallinity, providing excellent and consistent process- and product behaviour. The product comprises an advanced phenol free stabilizer package, providing superior gas fading resistance and inherent basic UV stability.

Applications

DuPure T 88 E is suitable for: continuous filaments (CF), high-resilience bulked continuous filaments (BCF), and fine denier staple fibres.

Quality, Environment and Safety Regulations

Material Safety Data Sheets and other regulatory documents are available on our web site <http://www.ducorchem.com>.

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(230 °C / 2.16 kg)	ISO 1133	25	g/10 min
Mechanical				
Tensile Modulus	(1 mm/min)	ISO 527-2	1500	MPa
Tensile Stress at Yield	(50 mm/min)	ISO 527-2	35	MPa
Tensile Strain at Yield	(50 mm/min)	ISO 527-2	8	%
Tensile Strain at Break	(50 mm/min)	ISO 527-2	> 50	%
Charpy Impact Strength, notched	(+23 °C)	ISO 179/1eA	2.5	kJ/m ²
	(-30 °C)	ISO 179/1eA	1.5	kJ/m ²
Charpy Impact Strength, unnotched	(+23 °C)	ISO 179/1eU	110	kJ/m ²
	(-30 °C)	ISO 179/1eU	13	kJ/m ²
Ball Indentation Hardness (H 358/30)		ISO 2039-1	78	MPa
Thermal				
Melting Point, DSC		ISO 3146	163	°C
Heat Deflection Temperature	(1.8 MPa)	ISO 75-2	55	°C
Heat Deflection Temperature	(0.45 MPa)	ISO 75-2	85	°C
Vicat Softening Temperature	(10 N)	ISO 306	154	°C
Vicat Softening Temperature	(50 N)	ISO 306	90	°C
Other Properties				
Density		ISO 1183	0.91	g/cm ³

* Typical values; not to be construed as specifications

Ducor Petrochemicals B.V., POB 1038, 3180AA Rozenburg ZH, the Netherlands
 Web: <http://www.ducorchem.com/>
 Email: sales@ducorchem.com

Last updated: September 2020

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Ducor Petrochemicals extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.